



中国认可
国际互认
检测
TESTING
CNAS L6319



中联品检（上海）技术服务有限公司
United Testing Services (Shanghai) Co., Ltd.

检测报告

防伪查询网址: www.fcl-sz.org.cn
防伪码: 6085368452



报告编号: ZLPJ10194987

第 1 页, 共 5 页

客户信息	委托单位 : 上海市梅园中学		
样品描述	藏青色针织长裤		样品数量: 1 条
客户认定信息	生产单位 : 江苏苏美达伊顿纪德品牌管理有限公司 客供成分 : 棉 80% 聚酯纤维 20% 样品名称 : 运动服下装		
样品获取	送样		
样品受理日期	2026-09-11	测试日期	2026-09-11~2026-09-12
检验性质	委托检测	报告签发日期	2026-09-12
判定依据	- GB 31701-2015 《婴幼儿及儿童纺织产品安全技术规范》 B 类 - GB/T 29862-2013 《纺织品 纤维含量的标识》 - GB/T 31888-2015 《中小学生校服》		
综合检验结论	检验结果及单项判定见下页。		
样品呈现	见末页。		

批准:

史进霞

制单:

许源



地址: 上海市松江区鼎源路 618 弄 1 号 29 幢 4、8 层及 1 号 30 幢地下室部分近车位 C005 左侧

Address: 4&8/F. of Building 29, No. 1, and Left Side, Near Parking Space C005, Basement Section, Building 30, No.1, Lane 618, Dingyuan Road, Songjiang District, Shanghai, China

邮编/Post Code: 201616 电话/Tel: 021-67877405 传真/Fax: 021-37657160

若对检测报告有异议, 应于收到报告之日起 15 日内向检测单位提出, 逾期不予受理。

Disagreement against the reports, if any, should be offered to United Testing Services (Shanghai) Co., Ltd. within 15 days since receiving this report.



中国认可
国际互认
检测
TESTING
CNAS L6319



中联品检（上海）技术服务有限公司
United Testing Services (Shanghai) Co., Ltd.

检测报告

防伪查询网址: www.fcl-sz.org.cn
防伪码: 6085368452



报告编号: ZLPJ10194987

第 2 页, 共 5 页

综合检验结论

序号	项目	判定依据	判定结果
1	异味	GB 31701-2015 B 类 GB/T 31888-2015	合格
2	残留金属针	GB/T 31888-2015	合格
3	附件锐利性	GB/T 29862-2013 GB/T 31888-2015	不适用
4	纤维含量	GB/T 29862-2013 GB/T 31888-2015	合格
5	耐水色牢度	GB 31701-2015 B 类 GB/T 31888-2015	合格
6	耐汗渍色牢度	GB 31701-2015 B 类 GB/T 31888-2015	合格
7	耐摩擦色牢度	GB 31701-2015 B 类 GB/T 31888-2015	合格
8	pH 值	GB 31701-2015 B 类 GB/T 31888-2015	合格
9	甲醛含量	GB 31701-2015 B 类 GB/T 31888-2015	合格
10	可分解致癌芳香胺染料	GB 31701-2015 B 类 GB/T 31888-2015	合格



地址: 上海市松江区鼎源路 618 弄 1 号 29 幢 4、8 层及 1 号 30 幢地下室部分近车位 C005 左侧

Address: 4&8/F. of Building 29, No. 1, and Left Side, Near Parking Space C005, Basement Section, Building 30, No.1, Lane 618, Dingyuan Road, Songjiang District, Shanghai, China

邮编/Post Code: 201616 电话/Tel: 021-67877405 传真/Fax: 021-37657160

若对检测报告有异议, 应于收到报告之日起 15 日内向检测单位提出, 逾期不予受理。

Disagreement against the reports, if any, should be offered to United Testing Services (Shanghai) Co., Ltd. within 15 days since receiving this report.



中国认可
国际互认
检测
TESTING
CNAS L6319



中联品检（上海）技术服务有限公司
United Testing Services (Shanghai) Co., Ltd.

检测报告

防伪查询网址: www.fcl-sz.org.cn
防伪码: 6085368452



报告编号: ZLPJ10194987

第 3 页, 共 5 页

测试项目（计量单位） [样品标识]	测试方法 （参数说明）	技术要求 （备注）	测试结果	判定
√ [1.整体]				
异味	GB 18401-2010 条款 6.7	无	无	合格
残留金属针	GB/T 24121-2009	符合 GB 31701-2015 条款 4.5.1、4.5.2 的要求	无锐利物	合格
附件锐利性	GB/T 31702-2015	--	不适用	--
√ [2.面料]				
纤维含量（%）	FZ/T 01057.2-2007 FZ/T 01057.3-2007 FZ/T 01057.4-2007 GB/T 2910.11-2024 （结合公定回潮率）	棉 80[±5] 聚酯纤维 20[±5]	棉 82.0 聚酯纤维 18.0	合格
	GB/T 31888-2015 条款 4.2.2	直接接触皮肤部分的 棉纤维含量标称值不 低于 35%	符合	
耐水色牢度（级）	GB/T 5713-2013	变色 ≥ 3-4 沾色 ≥ 3-4	变色 4-5 沾色 -棉 4-5 -聚酯纤维 4-5	合格
耐汗渍色牢度（级）	GB/T 3922-2013	酸性:变色 ≥ 3-4 酸性:沾色 ≥ 3-4 碱性:变色 ≥ 3-4 碱性:沾色 ≥ 3-4	(酸性)(碱性) 变色 4-5 4-5 沾色 -棉 4-5 4-5 -聚酯纤维 4-5 4-5	合格
耐摩擦色牢度（级）	GB/T 3920-2008	干摩擦 ≥ 3-4 湿摩擦 ≥ 3	干摩擦 4-5 湿摩擦 3	合格
pH 值	GB/T 7573-2009 （萃取介质：0.1mol/L 氯化钾溶液）	4.0~8.5	6.0	合格
甲醛含量（mg/kg）	GB/T 2912.1-2009 水萃取法	≤ 75	未检出	合格
	备注：1) “未检出”指小于检出限；2) 检出限：20mg/kg。			
可分解致癌芳香胺染料（mg/kg）	GB/T 17592-2024 GC-MS 分析方法	禁用(≤ 20)	未检出	合格
	备注：1) “未检出”指小于定量限；2) 定量限：5mg/kg；3) 禁用芳香胺物质清单见附页。			
备注	1. 本实验室根据客户要求完成以上检测内容，本检测报告的结果仅适用于来样。 2. 本实验室不对客户认定信息真实性负责。 3. 标记"--"的测试项目表示不予判定或不具备判定条件。 4. 除非客户要求，本报告不考虑测量结果的不确定度。			

地址: 上海市松江区鼎源路 618 弄 1 号 29 幢 4、8 层及 1 号 30 幢地下室部分近车位 C005 左侧

Address: 4&8/F. of Building 29, No. 1, and Left Side, Near Parking Space C005, Basement Section, Building 30, No.1, Lane 618, Dingyuan Road, Songjiang District, Shanghai, China

邮编/Post Code: 201616 电话/Tel: 021-67877405 传真/Fax: 021-37657160

若对检测报告有异议, 应于收到报告之日起 15 日内向检测单位提出, 逾期不予受理。

Disagreement against the reports, if any, should be offered to United Testing Services (Shanghai) Co., Ltd . within 15 days since receiving this report.





中国认可
国际互认
检测
TESTING
CNAS L6319



中联品检（上海）技术服务有限公司
United Testing Services (Shanghai) Co., Ltd.

检测报告

防伪查询网址: www.fcl-sz.org.cn
防伪码: 6085368452



报告编号: ZLPJ10194987

第 4 页, 共 5 页

附页:

No. (编号)	CAS No. (化学文摘编号)	Chemical Name (化学名称)
1	92-67-1	4-aminobiphenyl (4-氨基联苯)
2	92-87-5	benzidine (联苯胺)
3	95-69-2	4-chloro-o-toluidine (4-氯邻甲苯胺)
4	91-59-8	2-naphthylamine (2-萘胺)
5	97-56-3	o-aminoazotoluene (邻氨基偶氮甲苯)
6	99-55-8	5-nitro-o-toluidine (5-硝基-邻甲苯胺)
7	106-47-8	p-chloroaniline (对氯苯胺)
8	615-05-4	2,4-diaminoanisole (2,4-二氨基苯甲醚)
9	101-77-9	4,4'-diaminobiphenylmethane (4,4'-二氨基二苯甲烷)
10	91-94-1	3,3'-dichlorobenzidine (3,3'-二氯联苯胺)
11	119-90-4	3,3'-dimethoxybenzidine (3,3'-二甲氧基联苯胺)
12	119-93-7	3,3'-dimethylbenzidine (3,3'-二甲基联苯胺)
13	838-88-0	3,3'-dimethyl-4,4'-diaminobiphenylmethane (3,3'-二甲基-4,4'-二氨基二苯甲烷)
14	120-71-8	p-cresidine (2-甲氧基-5-甲基苯胺)
15	101-14-4	4,4'-methylene-bis- (2-chloroaniline) (4,4'-亚甲基-二- (2-氯苯胺))
16	101-80-4	4,4'-oxydianiline (4,4'-二氨基二苯醚)
17	139-65-1	4,4'-thiodianiline (4,4'-二氨基二苯硫醚)
18	95-53-4	o-toluidine (邻甲苯胺)
19	95-80-7	2,4-toluylenediamine (2,4-二氨基甲苯)
20	137-17-7	2,4,5-trimethylaniline (2,4,5-三甲基苯胺)
21	90-04-0	o-anisidine (邻氨基苯甲醚)
22	60-09-3	4-aminoazobenzene (4-氨基偶氮苯)
23	95-68-1	2,4-xylidine (2,4-二甲基苯胺)
24	87-62-7	2,6-xylidine (2,6-二甲基苯胺)



地址: 上海市松江区鼎源路 618 弄 1 号 29 幢 4、8 层及 1 号 30 幢地下室部分近车位 C005 左侧

Address: 4&8/F. of Building 29, No. 1, and Left Side, Near Parking Space C005, Basement Section, Building 30, No.1, Lane 618, Dingyuan Road, Songjiang District, Shanghai, China

邮编/Post Code: 201616 电话/Tel: 021-67877405 传真/Fax: 021-37657160

若对检测报告有异议, 应于收到报告之日起 15 日内向检测单位提出, 逾期不予受理。

Disagreement against the reports, if any, should be offered to United Testing Services (Shanghai) Co., Ltd. within 15 days since receiving this report.

检测报告

防伪查询网址: www.fcl-sz.org.cn
防伪码: 6085368452



报告编号: ZLPJ10194987

第 5 页, 共 5 页

送检样品原样



===== 检测报告结束 =====

有限公司



地址: 上海市松江区鼎源路 618 弄 1 号 29 幢 4、8 层及 1 号 30 幢地下室部分近车位 C005 左侧

Address: 4&8/F. of Building 29, No. 1, and Left Side, Near Parking Space C005, Basement Section, Building 30, No.1, Lane 618, Dingyuan Road, Songjiang District, Shanghai, China

邮编/Post Code: 201616 电话/Tel: 021-67877405 传真/Fax: 021-37657160

若对检测报告有异议, 应于收到报告之日起 15 日内向检测单位提出, 逾期不予受理。

Disagreement against the reports, if any, should be offered to United Testing Services (Shanghai) Co , Ltd . within 15 days since receiving this report.